



# ASP TIMBER FLOOR

Address: 40 Terra Cotta Drive, Blackburn 3130  
Tel: 03 – 9878 9488 Fax: 03 - 9878 1577  
Free call: 1800 006 096  
Email: [asptimberfloor@hotmail.com](mailto:asptimberfloor@hotmail.com)  
Website: [www.asptimber.com](http://www.asptimber.com)

---

## ASP Engineered Technical Specifications

### Dimension

1820x130.180.140x14/3mm  
With 25% random length boards

### Colour Range

Spotted Gum. Black Butt .Tasmanian Oak

### Hardness:

Spotted Gum has Janka Hardness Rating of 11 kN  
Black butt has janka hardness Rating of 9.9KN

Tasmanian Oak has janka hardness Rating of 5 KN

### Finish

Undistressed : 7 Layers Germany Treffert Finish- Polyurethane  
Distressed: 4 Layers Germany Teffert Finish- Polyurethane

### Moisture Content

8-10%

### VOC Emissions

<E1 , 0.02 mg/m Below World Health Organization Level  
Warranty  
Lifetime Structural Warranty and 25 years domestic Finish  
Warranty